

IN THE CLAIMS:

Please amend claim 1, and add new claims 8 and 9, as shown in the complete list of claims that is presented below.

1. (currently amended) An improved resin pulley formed at least in part of a resin composition, wherein the improvement comprises:

the resin composition contains a phenol resin as a base resin, and contains 20 to 50 % by weight of an inorganic powder having a Mohs hardness of not less than 6.5, 20 to 40 % by weight of a reinforcing fiber, and 1 to 5 % by weight of fluoro-resin powder having an average particle diameter of not more than 10 μm as a ~~lubricant~~ lubricant,

wherein the inorganic powder has a content ratio (% by weight) W_p , the reinforcing fiber has a content ratio (% by weight) W_f , and $W_p > W_f$.

2. (original) The resin pulley according to claim 1, wherein the inorganic powder is a spherical silica powder having an average particle diameter of not more than 30 μm .

Claim 3 (cancelled).

4. (original) The resin pulley according to claim 1, wherein the reinforcing fiber is a glass fiber.

5. (original) The resin pulley according to claim 1, wherein the phenol resin is a phenol resin having a number average molecular weight of 600 to 900.

6. (previously presented) The resin pulley according to claim 1, wherein the average diameter of the fluoro-resin powder is not less than 1 μm .

7. (previously presented) The resin pulley according to claim 1, wherein the ratio of the reinforcing fiber is 20 to 30 % by weight.

8. (new) The resin pulley according to claim 1, wherein the content ratio W_p of the inorganic powder is not less than 33% by weight.

9. (new) The resin pulley according to claim 1, wherein the phenol resin has a content ratio (% by weight) W_r , and $W_p > W_r$.